

Protective Coatings Epoxy Floor Primer

Version: v01 January 2025

Product Description

Protective Coatings Epoxy Floor Primer is a 2-pack solvent-based epoxy primer for deep penetration into concrete substrate and enhanced with adhesion promoter for improved adhesion. It is used on prepared concrete to seal the porosity of the concrete, provide deep penetration to enhance adhesion and re-strengthen weak concrete to prepare for top coat finishing

Recommended Use

Use as primer and intermediate coat of the epoxy and polyurethane system. Suitable for use on concrete and steel surfaces where high degree of chemicals, oil and abrasion resistance is required.

Drying Time	: Touch Dry	2 hours
	: Hard Dry	6 hours
	: Full Cure	7 Days
	: Recoat	4 hours

Technical Properties

Binder : Epoxy

Solids (% by Volume) : Approximately 42%

Flash Point : Part A (Paint) - About 31° C
Part B (Hardener) – About 31° C

Pot Life : About 5 to 6 hours

Colour : Grey

Finish : Gloss

Application Methods

Applied By : Brush / Roller / Spray

Thinner : General Thinner

Clean Up : General Thinner

Packaging & Storage

Packaging : 5L Set. 4L Part A (Paint) & 1L Part B (Hardener)

Shelf Life : 12 months - Unopened

Storage : Cool, dry and well-ventilated area away from heat and direct sun light. Lid must be kept tightly closed.

Application Information

Substrate: Concrete & Metal

Recommended No. of Coats: 1

Recommended Wet Film Thickness:
100 µm / Coat

Recommended Dry Film Thickness:
40 to 50 µm / Coat

Theoretical Coverage: 42 - 52 m²/ 5L Set
(Does not include substrate condition and loss factors)

Surface Preparation

Concrete Floor

The surface must be treated with about 5% sulphuric acid solution until effervescence has stopped. Then wash thoroughly with clean water and allow to dry completely before application of the epoxy floor coating.

TECHNICAL DATA SHEET

Steel Floor

For maximum performance, abrasive blasting is the most effective and economical method. However, when blast cleaning is impractical due to site and safety limitations, hand power tool cleaning to St 3 (ISO 8501-1:1988) is recommended. Care must be taken to avoid excessive burnishing of steel surfaces. Prior to painting, ensure steel surfaces is thoroughly free from any oil & grease residues and foreign matters.

Typical Recommended Painting System

Substrate: Concrete

System	Product	No. of Coats
Primer	Ecomaxx PC Epoxy Floor Primer	1
Finish	Ecomaxx PC Epoxy Floor Coating	2

Substrate: Steel

System	Product	No. of Coats
Primer	Ecomaxx PC Epoxy Floor Primer	1
Finish	Ecomaxx PC Epoxy Floor Coating	2

Application & Cleaning Instructions

Pour the hardener into the paint container under agitation at low speed.

Dilute with 10-30% thinner, if necessary, to improve workability.

Clean up equipment immediately after use.

Health & Safety

Ensure good ventilation during application and drying. Avoid contact with skin and eyes. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. After contact with skin, wash immediately with plenty of soap and water. During spray application, do not breathe in mist and wear suitable respiratory protective equipment. Keep out of reach of children.

Complementary Products

It is recommended to use the Graphenstone and Ecomaxx products for complementary actions, according to the required application, repair and/or finish. Please, refer to the relevant Technical Data Sheets.

Usage Warnings

None in particular for normal use and people who do not have special pathologies. Protect skin and eyes. Apply with good ventilation, do not inhale product. Keep out of reach of children.

Waste Management

Help protect the environment, do not throw waste through the drain and use the nearest recycling centre.

Responsible Gesture

Minimize the product waste by estimating the amount you will need. Recover the unused paint to give it a new use, keep it under the above stated storage conditions.

Safety Information

For information regarding safety, physical, ecological and toxicological information see the latest version of the product's Material Safety Data Sheet.

Disclaimer

The above information is given to the best of our knowledge based on laboratory testing and practical experiences. The information in this data sheet may be subject to changes from time to time and without notice due to production refinements arising from continuing research and evaluation programmes, which may occasionally result in marginal changes in the coating properties.